

Cu Aerial - Hard Drawn (Bare)

Cu Bare Aerial - Hard Drawn 40mm²

Contact

Sales and Customer Solutions
sales.nz@nexans.com


Nexans Ref.: ACUT70AA001AAAA

Country Ref.: 6174

Copper conductor. Made to AS 1746.

DESCRIPTION

The HDCu aerial has lower elongation and increased tensile rating compared to annealed copper conductors.



STANDARDS

National AS 1746

Cu Aerial - Hard Drawn (Bare)

Cu Bare Aerial - Hard Drawn 40mm²

Contact

Sales and Customer Solutions
sales.nz@nexans.com

CHARACTERISTICS

Construction characteristics

Conductor material Copper

Dimensional characteristics

Conductor cross-section 40 mm²

Stranding (No./mm) 19/1.63

Nominal overall diameter 8.2 mm

Approximate weight 0.36 kg/m

Mechanical characteristics

Minimum breaking load 16 kN

NOTE

1. Coefficient of linear expansion $17.0 \times 10^{-6}/^{\circ}\text{C}$.
2. Modulus of elasticity:
 - a. 119 GPa for seven (7) wire conductors.
 - b. 118 GPa nineteen (19) wire conductors.
 - b. 117 GPa for thirtyseven (37) wire conductors.

Current ratings are based on ambient temperature of 30°C, a maximum conductor temperature of 75°C, rural weathered, summer noon and intensity of solar radiation 1000 W/m².